



email: infofax@kcc.com www.kcprofessional.com



KLEENGUARD[®]A50 Product Description

Intended Use

KLEENGUARD® A50 Ultra Garments, Jacket & Trousers are

- Limited life protective clothing designed to protect the user from, liquid aerosols, spray and light splashing where the risk of chemical exposure is defined as low risk, such as agricultural spraying.
- Also offer protection against solid particles.
- Are treated to be antistatic.
- Experience low lint and therefore are suitable for tasks such as paint spraying cars and aircraft.
- Approved as Complex design (Category 3) equipment offering protection to the levels specified for Type 6 (performance requirements for chemical protective suits offering limited protective performance against liquid chemicals) and Type 5 (particulates) by CEN. Jackets & Trousers are certified Type PB[6] when worn separately, but when worn together meet the requirements for Type 6/5

Product Description

Kimberly-Clark has invested in garment design and in the development of materials specifically for protective clothing to be able to offer the user the ideal combination of protection with comfort. Wearing garments of high breathability can reduce the effects of heat stress and therefore maintaining the efficiency and effectiveness of the wearer.

The fabric

KLEENGUARD® A50 Garments are made from an engineered structure called SMS which was invented by Kimberly-Clark and initially used to offer medical staff protection with comfort in critical conditions. The fabric has been developed to suit it for the challenges of industrial applications. The 3 layers of the fabric are made up of polyolefin fibres, which are carefully engineered to deliver a combination of strength, durability and protection. The outer layers use large strong fibres to resist wear and tear and protect the central core layer. The centre of the structure is made up of closely packed fine fibres, which act as a highly efficient filter to particles and as a barrier to many liquids. The fabric is treated to ensure liquid repellency and antistatic properties.

The seams

To provide high strength seams with barrier properties serged seams are used with triple overlock stitching.

The Zip

High quality full-length zips are used with stoppers to prevent strain.

Silicone Free

All components are carefully selected and specified as silicone free – an important reassurance for anyone working with paint or sensitive surfaces.

Symbols and Marking on the garment - what they tell you

KleenGuard

Kimberly-ClarkPROFESSIONAL*

www.kcprofessional.com

email: infofax@kcc.com

INFO



Product Performance Data

To be certified as a Type 5 and Type 6 chemical protective garment, KLEENGUARD® A50 Ultra must meet certain performance requirements laid down by CEN, the European committee for normalisation. The standards apply throughout all member states of the EU.

For each property test data is classified into bands indicted by a CLASS number on a scale where 1 is lowest. There are a different number of classes for different tests. For some tests a simple pass /fail result is given.

The product performance data for KLEENGUARD® A50 Ultra is shown below.

Limited Use Chemical Protective Clothing (Type 5&6)

Property	Test Method	Class/Result
Abrasion Resistance	EN 530 M2	Class 2 Visual

B Kimberly-Clark PROFESSIONAL*



www.kcprofessional.com



BRAND		ww.kcproressional.com
Stability to Heat	ISO 5978	Class 2 No Blocking
Flex Cracking Resistance	ISO 7854 M B	Class 1
Trapezoidal Tear Resistance	ISO 9073-4	Class 1 / 2*
Burst Resistance	ISO 2960	Class 1
Puncture Resistance	EN 863	Class 1
Repellence to Liquids	EN ISO 6530	10%NaOH Class 3
		$30\%H_2SO_4$ Class 3
Resistance to Penetration by Liquid Chemicals	EN ISO 6530	10%NaOH Class 3
Chemicals		30%H ₂ SO ₄ Class 3
Resistance to Ignition	EN 13274-4 MTH 3	PASS
Seam Strength	ISO 5082	Class 3
Resistance to Penetration by Liquids (spray test)	EN ISO 17491-4	PASS
Surface Resistivity	EN1149-1 1996	PASS
Determination of resistance of suits to penetration by aerosols and fine	EN ISO 13982-2	Average 6.4%
particles		Ave + 2SD 19.4%

Type 6 to EN 13034 :2005

Type 5 to prEN ISO 13982-1: 2004

DEDICATED TO PROTECTING YOU

?