

## PRODUCT SHEET

## SIVORI S1 P SRC

Prod. Ref. 78410-001 Safety cat. S1 P SRC Range of sizes 35 - 48 (2 - 13) Weight (sz. 8) 530 q Shape

Width

Α

11

Description: Blue punched suede leather shoe, SANY-DRY® lining, antistatic, anti-shock, slipping resistant, non metallic APT Plate midsole Zero Perforation

Plus: COFRA SOFT footbed, made of scented polyurethane, holed, antistatic, anatomic, soft and comfortable; the shape of the bottom part guarantees impact energy absorption (shock absorber) and high grip; the upper part absorbs moisture and keeps the foot dry. Perfumed sole. Excellent breathability

Suggested uses: Warehouses, transportation sector, industries

Care and maintenance: Clean after each use and dry off away from direct heat; treat the leather with a suitable shoe-polish. Avoid contact with aggressive chemicals or extreme temperature. Avoid immersion in sea water, lime water or cement mixed with water.



## MATERIALS / ACCESSORIES

## SAFETY TECHNICAL SPECIFICATIONS

			Clause EN ISO 20345:2011	Description	Unit	Cofra result	Requirement
Complete shoe	Toe cap: AL	UMINIUM made, ultra light, impact resistant until 200 J	5.3.2.3	Shock resistance (clearance after shock)	mm	15,5	≥ 14
	an	d compression resistant until 1500 kg	5.3.2.4	Compression resistance (clearance after compression)	mm	15	≥ 14
	•	tion midsole: in multi-layers highly tensile fabric, penetration resistant, Zero	6.2.1	Penetration resistance	N	To 1100 N	≥ 1100
	Perforation					No perforation	
	Antistatic shoe: the bottom is fit for the dissipation of electrostatic charges		6.2.2.2	Electric resistance			
				- wet	$M\Omega$	388	≥ 0.1
				- dry	$M\Omega$	706	≤ 1000
	Energy absorption system		6.2.4	Shock absorption	J	28	≥ 20
Upper	Blue suede leather		5.4.6	Water vapour permeability	mg/cmq h	> 4,5	≥ 0,8
	thickness 1,6/1,8 mm			Permeability coefficient	mg/cmq	> 42,8	> 15
Vamp	Textile, breathable, abrasion resistant, colour black		5.5.3	Water vapour permeability	mg/cmq h	> 6,3	≥ 2
lining	Thickness 1,2 mm			Permeability coefficient	mg/cmq	> 51,1	≥ 20
Quarter	SANY-DRY®, antibacterial, breathable, abrasion resistant, colour yellow		5.5.3	Water vapour permeability	mg/cmq h	> 10,3	≥ 2
lining	thickness 1,2 mm			Permeability coefficient	mg/cmq	> 82,8	≥ 20
Sole	Antistatic Polyurethane/TPU directly injected in the upper:		5.8.3	Abrasion resistance (lost volume)	$\text{mm}^3$	37	≤ 150
	Outsole:	Ice TPU, slipping resistant, abrasion resistant and hydrocarbons resistant.	5.8.4	Flexing resistance (cut increase)	mm	1	≤ 4
	Midsole:	Blue polyurethane, low density, comfortable and anti-shock.	5.8.5	Interlayer bond strength	N/mm	> 5	≥ 4
			6.4.2	Hydrocarbons resistance ( $\Delta V$ = volume increase)	%	-0,6	≤ 12
	Adherence coefficient of the sole		5.3.5	SRA : ceramic + detergent solution – flat		0,60	≥ 0,32
				SRA : ceramic + detergent solution – heel (contact angle 7°)		0,52	≥ 0,28
				SRB : steel + glycerol – flat SRB : steel + glycerol – heel (contact angle 7°)		0,28	≥ 0,18
						0,19	≥ 0,13